

(19)



Europäisches Patentamt

European Patent Office

Office européen des brevets



(11)

EP 1 426 090 A1

(12)

EUROPEAN PATENT APPLICATION

(43) Date of publication:

09.06.2004 Bulletin 2004/24(51) Int Cl.7: **B01D 39/16, A47L 9/14**(21) Application number: **02027313.2**(22) Date of filing: **06.12.2002**

(84) Designated Contracting States:

**AT BE BG CH CY CZ DE DK EE ES FI FR GB GR
IE IT LI LU MC NL PT SE SI SK TR**


Designated Extension States:

AL LT LV MK RO(71) Applicant: **Eurofilters N.V.****3900 Overpelt (BE)**

(72) Inventors:

• **Sauer, Ralf c/o Eurofilters N.V.****3900 Overpelt (BE)**• **Schultink, Jan c/o Eurofilters N.V.****3900 Overpelt (BE)**(74) Representative: **Grünecker, Kinkeldey,****Stockmair & Schwanhäusser Anwaltssozietät****Maximilianstrasse 58****80538 München (DE)**(54) **Non-woven layer for a filter and composite layer incorporating said non-woven layer**

(57) The invention is directed to a nonwoven layer for a filter, in particular, for a vacuum cleaner bag, wherein at least one region of the nonwoven layer, the region having a predetermined thickness and a predetermined area, has an average pore size smaller than 50 μm and comprises fibers being bonded together such that a movement of the fibers relative to each other in a direction parallel to the surface of the layer is inhibited. The invention is further directed to a method for producing such a nonwoven layer.

**Fig. 1**

Description

[0001] The invention is directed to a nonwoven layer for a filter, in particular, for a vacuum cleaner bag.

[0002] Nowadays, many vacuum cleaner bags comprise composites of nonwoven materials instead of conventional filter paper, these composite materials showing a high filtration efficiency and capacity.

[0003] EP 0 960 645 discloses such a prior art vacuum cleaner bag. This prior art construction is made of three layers, namely, in the direction of the air flow, a bulky meltblown, a meltblown fleece and a spunbond or spunlace layer. The upstream bulky meltblown layer which will be located at the inner side of the bag serves to remove larger dust particles and to hold the dust in its structure.

[0004] The prior art filter structures have a high filtration efficiency. However it turned out in practice that elongated particles or objects with small diameters such as hairs (having a diameter of about $70.2 \pm 12.3 \mu\text{m}$) tend to penetrate the filter. This penetration mainly occurs in the region where the stream of air of the vacuum cleaner meets the wall of the filter bag. The elongated objects act like spears and pierce the filter structure. Although these elongated objects usually do not exit the filter bag, many of them stick out of the outermost layer of the bag. Therefore, these objects are visible from the outside, which is aesthetically disturbing.

[0005] In view of this, it is the problem underlying the invention to provide a material that is suitable for use in a filter and has a better retention regarding elongated particles and objects.

[0006] This problem is solved by a filter comprising the features of claim 1. Accordingly, the invention provides a nonwoven layer for a filter, in particular, for a vacuum cleaner bag, wherein at least one region of the nonwoven layer, the region having a predetermined thickness and a predetermined area, has an average pore size smaller than $50 \mu\text{m}$ and comprises fibers being bonded together such that a movement of the fibers relative to each other in a direction parallel to the surface of the layer is inhibited.

[0007] Surprisingly, it was found that a nonwoven layer having these features reduces the above-mentioned problem of penetration while maintaining a desired air permeability to a high degree. The at least one region can be chosen so as to correspond only to the area where a stream of air meets the nonwoven layer. Alternatively, the at least one region can be the whole area of the nonwoven layer. The thickness of the region may range from a thickness of the order of magnitude of one fiber diameter up to the total thickness of the nonwoven layer.

[0008] Such a bonding of the fibers has the effect that an elongated object striking the nonwoven layer is inhibited or even prevented of displacing the fibers in a direction parallel to the surface of the layer. This would happen with loose fibers that are not bonded in such a

way. Therefore, the penetration of the elongated objects is reduced or prevented.

[0009] However, it is not necessary that two fibers are bonded to one another at each point where they are touching or crossing each other. In some cases it is also sufficient if the fibers are bonded only at some crossing points.

[0010] According to a preferred embodiment, the nonwoven layer can be an airlaid and/or carded nonwoven layer, a spunbond or spunlace nonwoven layer or a meltblown nonwoven layer.

[0011] Advantageously, any of the above-described nonwoven layers can have a basis weight between 10 and 100 g/m^2 and the spunbond or spunlace fibers can have an average fineness of 0.6 to 12 denier, the meltblown fibers can have an average diameter of $1 \mu\text{m}$ to $15 \mu\text{m}$ and the carded fibers can have an average fineness of 1 - 16.7 denier. These diameters ensure excellent filtration and air permeability properties.

[0012] According to a preferred embodiment of the above-described nonwoven layers, the at least one region can comprise an adhesive. This adhesive enables the bonding of the fibers in a very efficient manner.

[0013] According to a preferred embodiment, the adhesive can be a hot melt, a cold glue, a dry bond adhesive and/or a thermoplastic polymer, preferably a pulverized polymer. In the case of a hotmelt, preferably one additional layer covers the tacky hotmelt. An example of a thermo-plastic pulverized polymer is a pulverized polyolefin.

[0014] In an advantageous embodiment, the amount of hotmelt can be between 1 and 10 g/m^2 . In a more preferred embodiment, the basis weight of the hotmelt is approximately 3 - 5 g/m^2 . Such a basis weight guarantees, on the one hand, a high penetration reduction and, on the other hand, still sufficient air permeability.

[0015] According to an alternative advantageous embodiment, the at least one region can be a hot calendared region.

[0016] The above-described nonwoven layers can be implemented in a filter composite in form of an additional layer. Alternatively, layers already present in a filter, such as a filter layer (for example meltblown layer), a support layer (for example a spunbond layer) or the like can be provided with fibers bonded together such that the movement of the fibers is inhibited.

[0017] The invention also provides a composite layer for a filter, in particular, for a vacuum cleaner bag comprising:

a first nonwoven layer according to one of the previously described nonwoven layers, and

a second nonwoven layer on top of the first nonwoven layer,

wherein an adhesive is located at an interface between the first and second nonwoven layer such that fibers of

the first and/or the second nonwoven layer are bonded together and a movement of the fibers in the first and/or second nonwoven layer relative to each other in a direction parallel to the surface of the layer is inhibited.

[0018] Thus, the fibers in such a composite layer are bonded together within one layer, within each one of the layers and/or between the two layers.

[0019] According to a preferred embodiment, the first or the second nonwoven layer is a spunbond nonwoven layer, the other nonwoven layer is a meltblown nonwoven layer, and the adhesive is a hotmelt. Such a structure guarantees excellent filtration properties since the meltblown layer may act as filter and the spunbond layer may act as a support layer and the combination of both layers avoids penetrating of elongated objects through the structure.

[0020] The invention further provides a method for producing a nonwoven layer as described above comprising the step of:

treating at least on region of the nonwoven layer, the region having a predetermined thickness and a predetermined area, such that the nonwoven layer has an average pore size smaller than 50 μm and such that the fibers are bonded together and a movement of the fibers relative to each other in a direction parallel to the surface of the layer is inhibited.

[0021] According to the preferred embodiment, the treating step comprises the steps of:

spraying of hotmelt, cold glue, dry bond adhesive and/or thermoplastic polymer, preferably pulverized polymer, and

applying pressure to obtain a bonding of the fibers.

[0022] According to an alternative advantageous method, the treating step comprises the step of hot calendering.

[0023] The invention also provides a method for producing a composite layer as described above comprising the steps of:

providing a first nonwoven layer,

applying an adhesive to the first nonwoven layer, and

providing a second nonwoven layer,

wherein the adhesive is located at an interface between the first and second nonwoven layer such that fibers of the first and/or the second nonwoven layer are bonded together and a movement of the fibers in the first and/or second nonwoven layer relative to each other in a direction parallel to the surface of the layer is inhibited.

[0024] According to a preferred embodiment, this method further comprises the step of applying pressure to obtain a bonding of the fibers. In this way, an improved bonding of the fibers can be obtained.

[0025] Further features and advantages of the invention are described with reference to the drawings.

Figure 1 shows a sectional view of a first example of a composite layer in accordance with the invention.

Figure 2 shows a sectional view of a second example of a composite layer in accordance with the invention.

[0026] Figure 1 shows a section of an example of a three-layer composite. The direction of the airflow is indicated by an arrow. The first upstream layer is a bulky meltblown or air laid layer 1 by a meltblown fleece 2. Downstream, the meltblown fleece 2, a spun bond layer 3 is located. At the interface between meltblown fleece 2 and spunbond layer 3, hotmelt 4 is located. Due to the hotmelt, the fibers in the spunbond layer 3 and the meltblown layer 2 are bonded together and, thus, kept in a relatively fixed position. Incoming elongated objects such as hairs may penetrate the bulky meltblown 1 and meltblown 2. At the interface between meltblown 2 and spunbond 3, the fibers within each layer and between the layers are bonded together due to the hotmelt. Due to this bonding together, the pore size in the region of the bonded fibers is less than 50 μm , preferably 15 μm . Therefore, a relative displacement of the fibers at the interface is inhibited or even prevented; a further penetration of the hairs is avoided. In this example, the treated region extends over the whole area of the nonwoven layer. The thickness of the region is very small; only fibers situated at the interface are bonded together. Thus, the thickness is of the order of magnitude of some fiber diameters. Of course, the thickness of the treated region can be increased if desired and necessary.

[0027] An alternative example is shown in Figure 2. The structure of the composite is the same as in the first example. However, no hotmelt is present. Instead of the hotmelt, the spunbond 3 was hot calendered. This calendering results in a modified region 5 where the fibers are bonded together. According to a preferred embodiment, the spunbond 3 is a polypropylene having a basis weight of approximately 65 g/m² and an average fineness of about 2.5 denier or a basis weight of approximately 25 g/m² and an average fineness of about 0.9 denier. Then, preferred process parameters for the calender step are a pressure of 5 bar, a temperature of 160° C and a speed of 10 - 20 m/min. In this example, only a selected area of the spunbond is treated. The thickness of the region, however, corresponds to the whole thickness of the spunbond layer 3. Therefore, in a final vacuum cleaner bag, this region preferably is to be placed where the incoming airflow strikes the bag.

[0028] It is to be understood that a nonwoven layer according to the invention can be used in other composite structures as well.

Claims

1. Nonwoven layer for a filter, in particular, for a vacuum cleaner bag, **characterized in that** at least one region of the nonwoven layer, the region having a predetermined thickness and a predetermined area, has an average pore size smaller than 50 μm and comprises fibers being bonded together such that a movement of the fibers relative to each other in a direction parallel to the surface of the layer is inhibited. 5
2. Nonwoven layer according to claim 1 wherein the nonwoven layer is an airlaid and/or carded nonwoven layer, a spunbond or spunlace nonwoven layer, or a meltblown nonwoven layer. 10
3. Nonwoven layer according to claim 2 having a basis weight between 10 and 100 g/m² and wherein the spunbond fibers have an average fineness of 0.6 - 12 denier, the meltblown fibers have an average diameter of 1 μm - 15 μm , and the carded fibers have an average fineness of 1 - 16.7 denier. 15
4. Nonwoven layer according to one of the preceding claims wherein the at least one region comprises an adhesive. 20
5. Nonwoven layer according to claim 4 wherein the adhesive is a hotmelt, a cold glue, a dry-bond adhesive, and/or a thermoplastic polymer, preferably a pulverized polymer. 25
6. Nonwoven layer according to claim 5 wherein the amount of hotmelt is between 1 and 10 g/m². 30
7. Nonwoven according to one of the claims 1 - 3 wherein the at least one region is a hot calendered region. 35
8. Composite layer for a filter, in particular, for a vacuum cleaner bag, comprising: 40
 - a first nonwoven layer according to one of the claims 1 - 6, and
 - a second nonwoven layer on top of the first nonwoven layer,
 wherein an adhesive is located at an interface between the first and second nonwoven layer such that fibers of the first and/or the second nonwoven layer are bonded together and a movement of the
9. Composite layer according to claim 8 wherein the first or second nonwoven layer is a spunbond nonwoven layer, the other nonwoven layer is a meltblown nonwoven layer, and the adhesive is a hotmelt. 45
10. Method for producing a nonwoven layer according to one of the claims 1 - 7 comprising the step of:
 - treating at least one region of the nonwoven layer, the region having a predetermined thickness and a predetermined area, such that the nonwoven layer has an average pore size smaller than 50 μm and such that the fibers are bonded together and a movement of the fibers relative to each other in a direction parallel to the surface of the layer is inhibited. 50
11. Method according to claim 10 wherein the treating step comprises the steps of:
 - spraying of hotmelt, cold glue, dry-bond adhesive, and/or thermoplastic polymer, preferably pulverized polymer, and
 - applying pressure to obtain a bonding of the fibers. 55
12. Method according to claim 10 wherein the treating step comprises the step of hot calendering.
13. Method for producing a composite layer according to claim 8 or 9 comprising the steps of:
 - providing a first nonwoven layer,
 - applying an adhesive to the first nonwoven layer, and
 - providing a second nonwoven layer,
 wherein the adhesive is located at an interface between the first and second nonwoven layer such that fibers of the first and/or the second nonwoven layer are bonded together and a movement of the fibers in the first and/or second nonwoven layer relative to each other in a direction parallel to the surface of the layer is inhibited.
14. Method according to claim 13 further comprising the step of applying pressure to obtain a bonding of the fibers.




Fig.1




Fig.2



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 02 02 7313

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (m.C.I.7)
X A	EP 0 338 479 A (GESSNER & CO GMBH) 25 October 1989 (1989-10-25) * page 3, line 27 - line 57 *	1-3, 7, 10, 12 8, 9, 13, 14	B01D39/16 A47L9/14
X A	US 6 193 773 B1 (SCHLOER ULRICH ET AL) 27 February 2001 (2001-02-27) Detailed Description	1, 2, 7, 10, 12 8, 9, 13, 14	
X A	US 5 855 992 A (ETZOLD STEFAN) 5 January 1999 (1999-01-05) * the whole document *	1-3, 7, 10, 12 8, 9, 13, 14	
X A	WO 01 12427 A (FIRST QUALITY FIBERS INC) 22 February 2001 (2001-02-22) * page 2, line 21 - page 14, line 21; figures *	1, 2, 7, 10, 12, 13 8, 9, 14	TECHNICAL FIELDS SEARCHED (m.C.I.7) B01D A47L D04H
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 23 January 2003	Examiner Plaka, T
<p>CATEGORY OF CITED DOCUMENTS</p> <p>X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document</p> <p>T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document</p>			

EPO FORM 1508 03 02 (P04C01)

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 02 02 7313

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

23-01-2003

Patent document cited in search report		Publication date	Patent family member(s)		Publication date
EP 0338479	A	25-10-1989	DE	3812849 A1	26-10-1989
			AT	79782 T	15-09-1992
			DE	58902112 D1	01-10-1992
			EP	0338479 A1	25-10-1989
			ES	2035409 T3	16-04-1993
US 6193773	B1	27-02-2001	DE	19832611 A1	03-02-2000
			EP	0974387 A1	26-01-2000
			JP	3335141 B2	15-10-2002
			JP	2000042324 A	15-02-2000
			KR	2000011861 A	25-02-2000
			TR	9901675 A2	21-02-2000
US 5855992	A	05-01-1999	DE	19642958 A1	23-04-1998
			AT	217539 T	15-06-2002
			CN	1182145 A ,8	20-05-1998
			DE	59707270 D1	20-06-2002
			DK	836877 T3	09-09-2002
			EP	0836877 A1	22-04-1998
			ES	2175242 T3	16-11-2002
			JP	10204765 A	04-08-1998
WO 0112427	A	22-02-2001	AU	6630400 A	13-03-2001
			CN	1382083 T	27-11-2002
			EP	1218170 A1	03-07-2002
			WO	0112427 A1	22-02-2001
			US	2002036062 A1	28-03-2002

EPO FORM P0412

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82